



WHERE QUALITY, SERVICE & INTEGRITY MEET.

Phone (219)310-8645 Fax (219)662-0410 Email: [info@heartland-adhesives.com](mailto:info@heartland-adhesives.com)

## **FAS-LOK 62**

### **Anaerobic Thread Locking Compound**

**FAS-LOK 62** is a fast curing, high strength, anaerobic thread-locking compound for bonding and sealing threads, and retaining of cylindrical parts.

**FAS-LOK 62** is highly resistance to heat, vibrations, water, gases, oils, hydrocarbons and many chemicals.

#### **Applications:**

- Designed for permanent locking & sealing of threaded fasteners.
- Ideal for thread locking large bolts and studs from loosening under vibration.
- Meets Military specifications: Mil-S-46163 TYPE II Grade O
- Meets ASTM D5363 AN0331

#### **Physical Properties:**

Composition:	Methacrylate Ester
Color:	Red
Viscosity:	1500 cps at 25 °C
Specific Gravity:	1.05
Flash Point:	> 100°C
Solvent Content:	None
Shelf Life:	1 year

#### **Curing Properties:**

Handling Cure Time:	5-10 minutes
Functional Cure Time:	1-2 hours
Full Cure Time:	12 hours
Temperature Range	-65 to 350°F
Locking Torque*	
--Break @ 72°F	185 in lbs.
--Prevailing @72°F	400 in lbs.

\* Per ASTM D5363 Specification.

3/8-16 plain finish cap screws and nuts.

Larger fasteners will increase surface area and breakaway torque.

FasLok 71 meets ASTM D5363 AN0331 and Mil-S-46163 TYPE II Grade O

## **Chemical Resistance:**

Chemical	Temp.	% Initial Strength Retained	
		500 hours	1000 hours
Acetone	22 °C	100	90
Ethanol	22 °C	100	100
Motor Oil	125 °C	100	100
Gasoline	22 °C	100	100
Brake Fluid	22 °C	100	100
Water/Glycol	87 °C	90	80

## **Application Method:**

Surfaces should be dry, clean, and free of any contamination. Thread locker should be applied to the bolt in sufficient quantity to fill threads. This thread locker is specifically formulated to give controlled friction and torque/tension ratio during assembly.

## **Storage:**

Anaerobic adhesives shall be ideally stored in a cool, dry place in unopened containers at a room temperature between 46 °F to 70 °F. Please do not return any unused material to its original container.

**PRECAUTIONS:** This product and the auxiliary materials normally combined with it are capable of producing adverse health effects ranging from minor skin irritation to serious systemic effects. None of these materials should be used, stored, or transported until the handling precautions and recommendations as stated in the Material Safety Data Sheets (MSDS) for this and all other products being used are understood by all persons who will work with the material.

**Warranty:** Heartland warrants only that its product will meet those specifications designated as such herein or in other publications. All other information supplied by Heartland is considered accurate but are furnished upon the express condition the customer shall make its own assessment to determine the product's suitability for a particular purpose. Heartland makes no other warranty, either express or implied, including those regarding such other information, the data upon which the same is based, or the results to be obtained from the use thereof; that any product shall be merchantable or fit for any particular purpose; or that the use of such other information or product will not infringe any patent.